

Silicone Extrusions - Steam Resistant / Technical Data Sheet

Properties	Test Method	Value	Unit
Density	DIN 53 479A	1.11	-
Hardness	-	60	Shore A \pm 5
Tensile Strength	-	7.5	N/mm
Elongation @ Break	-	300	%
Tear Strength	-	10	N/mm
Rebound Resilience	-	65	%
Compression Set	-	8	%
Maximum Temperature	-	250	$^{\circ}$ C

Additional Information

This grade has been developed especially for the manufacture of articles with good resistance to steam. Suitable in particular for autoclave gaskets, steampot gaskets etc. Suitable for repeated use in contact with food and complies with FDA and BgW regulations.

All recommendations and information contained on this data sheet are, to the best of our knowledge, correct. Product specifications are intended as guidelines. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product design and properties without notification.