

## Silicone Extrusions - Low Temperature / Technical Data Sheet

Properties	Value	Unit
Density	1.22	-
Hardness	63	Shore A $\pm$ 5
Tensile Strength	9.8	N/mm
Elongation	730	%
Tear Strength	40.4	N/mm
Compression Set	29	%
Minimum Temperature	-100	$^{\circ}$ C

### Additional Information

This grade is designed to provide extended low temperature service. It provides low temperature flexibility to  $-100^{\circ}$ C ( $-148^{\circ}$ F).

All recommendations and information contained on this data sheet are, to the best of our knowledge, correct. Product specifications are intended as guidelines. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product design and properties without notification.